

Technical Data Sheet

Date of Issue: 1st May 2020

Page 1 of 3

Product Name: RELINFORCE EP Inject MI

Two component low viscous moisture insensitive Epoxy Injection Grout for strengthening of concrete substrates.

Description

RELINFORCE EP Inject MI is a two-component solvent free low viscous epoxy grout system for injection into cracks in concrete substrate & strengthening of concrete structures. It is mainly used in moisture sensitive areas.

Applications

- Sealing of cracks up to 5mm width.
- Sealing of pours in natural stones
- Fill voids in concrete Substrate to strengthen the matrix.
- Industrial heavy-duty floor toppings

Features & Benefits

- Adheres to Concrete & Mild Steel Surface well.
- Solvent Free
- Pre-weighted packing: No onsite proportioning required
- Low Viscous property allows the product to travel to smallest crevices in concrete, seal the pores & strengthen the core of concrete.
- Easy to inject

Mechanical Properties

Compressive Strength @ 25 ^o C (As per IS 6746) 7 Days	> 60 MPa
Tensile Strength @ 25 ^o C (As per ASTM D638) 7 Days	> 20 MPa
Flexural Strength @ 25 ^o C (As per ASTM D 790) 7 Days	> 20 MPa
Bond Strength @ 25 ^o C Concrete	> 2 MPa (Concrete Failure)

Technical Data Sheet

Date of Issue: 1st May 2020

Page 2 of 3

Component Details & Physical Property

	Part A	Part B	Mixed
Feel	Liquid	Liquid	Liquid
Color	Transparent	Pale Yellow	Pale Yellow
Mixing Ratio	100	50	-
Viscosity @ 250 C	500 -1000	500 - 1000	500 - 1000
Density	1.10 - 1.15	1.00 - 1.05	1.10 - 1.15
*Pot Life @ 25 ^o C, 100 gm mass			40 – 60 mins
Change in Volume			No Shrinkage Observed
Yield (Pack)	4 kg	2 kg	6 kg

* Ambient Temperature will affect the Pot life & Setting Time of the Product & is inversely related

Mixing Procedure

- Full Pack Mixing is ideally suggested for accurate result
- Part Mixing suggested only if precise proportioning facility available at site.
- Mechanical Mixing using low speed stirrer is suggested.
- Mixing till uniform color achieved of the mixed material.

Application Procedure

- Surface to be clean of Oil, Grease, dust, curing compound & any other material which will affect the adhesion of *RELINFORCE EP Putty* to Substrate
- *RELINFORCE EP Putty* to be used to fix the appropriate Nozzle to concrete substrate
- Nozzle spacing to be as per the specification given by the structural consultant
- Injection Process to be carried out in sequence from lower port to higher port on a continual path basis.

Packaging Size

- Part A : 4 kg
- Part B : 2 kg

Shelf Life

- Part A : 12 Months
- Part B : 12 Months

Technical Data Sheet

Date of Issue: 1st May 2020

Page 3 of 3

Storage Condition

- Material to be stored in cool dry place
- To be kept under shade with no direct sunlight

Health & Safety Hazard Condition

Please refer to MSDS for detailed information on the health & safety hazard while using the product.

Notice: No freedom from any patent owned by RIL or others is to be inferred. RIL assumes no obligation or liability for the information in this document. The information provided herein is presented in good faith and is based on the best of RIL's knowledge, information, and belief. Since use conditions at non-RIL facilities are beyond RIL's control and government requirements may differ from one location to another and may change with time, it is solely the Buyer's responsibility to determine whether RIL's products are appropriate for the Buyer's use, and to assure the Buyer's workplace, use, and disposal practices are in compliance with applicable government requirements. Consequently, RIL assumes no obligation or liability for use of these materials and makes no warranty, express or implied. The user of the information provided is solely responsible for compliance with any applicable government requirements. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

Vadodara Composites Division, Village: Asoj, Vadodara-Halol Expressway, Taluka: Waghodia, Vadodara, Gujarat 391510